



Composition:

- Inner tube: thermoplastic polymer
- Reinforcement: one or two braids of synthetic fiber plus one special extra braid of synthetic fiber.
- Cover: polyurethane, blue

Working temperature: From -40° to +60° C.

Part n°	DN	Ø in	Ø out	Working Pressure (bar)	Working pressure (psi)	Burst pressure (bar)	Burst pressure (psi)	Bending radius (mm)	Weight (kg/m)	LONGITUD (M)
MTREC2001280	3/4"	19,6	29,7	200	2.900	500	7.200	120	0,415	80
MEC20012	3/4"	19,6	29,7	200	2.900	500	7.200	120	0,415	120
MTREC20012	3/4"	19,6	29,7	200	2.900	500	7.200	120	0,415	120
MEC20012160	3/4"	19,6	29,7	200	2.900	500	7.200	120	0,415	160
MTREC20012160	3/4"	19,6	29,7	200	2.900	500	7.200	120	0,415	160
MTREC2001680	1"	25,6	37,5	200	2.900	500	7.200	155	0,568	80
MTREC20016	1"	25,6	37,5	200	2.900	500	7.200	155	0,568	120
MTREC20016160	1"	25,6	37,5	200	2.900	500	7.200	155	0,568	160